

گريدهای وایتون	A	B	F	GF	GLT	GFLT	XLT	ULT	ETP	AFLAS®	BRFKM
قيمت نسبي	\$	\$\$	\$\$	\$\$	\$\$	\$\$\$	\$\$\$\$	\$\$\$\$\$	\$\$\$\$\$	\$\$	\$\$
در دسترس بودن											
H2S %	2	5	5	5	5	5	10	10	5	20	40
در شرایط ایستاتیک / عملکرد در دمای (C°) F° بالا	437 (225)	437 (225)	437 (225)	437 (225)	437 (225)	437 (225)	437 (225)	437 (225)	437 (225)	450 (232)	450 (232)
(C°) F° عملکرد در دمای پایین در شرایط ایستاتیک	-15 (-26)	-11 (-24)	1 (-17)	3 (-16)	-40 (-40)	-29 (-34)	-54 (-48)	-65 (-54)	-6 (-21)	25 (-4)	1 (-17)
TR-10 LOW TEMPERATURE FLEXIBILITY F° (C°)	1 (-17)	7 (-14)	20 (-7)	21 (-6)	-22 (-30)	-11 (-24)	-40 (-40)	-49 (-45)	12 (-11)	37 (3)	20 (-7)
STRONG BASE, HIGH PH, CAUSTIC, AMINES											
LOW MOLECULAR WEIGHT CARBONYLS 100% CONCENTRATION (MTBB, MBK, MIBK, ETC.)											
ENGINE LUBRICATING OIL, SG AND SH											
AQUEOUS FLUIDS, STEAM, MINERAL ACIDS (H2SO4, HNO2)											
AROMATIC HYDROCARBONS (TOLUENE, ETC.)											
AUTOMOTIVE FUELS OXYGENATED WITH MEOH, ETOH, MTBE, ETC.											
ENGINE LUBRICATING OIL, SE AND SF											
مقاومت به مانای فشار											
اکثر سوخت های هواپیما و صنایع خودوربی											



= عالی



= خوب



= توصیه نمی گردد.